

TECHNICKÝ LIST A NÁVOD K POUŽITÍ

Položka č.	Název	Šířka	Délka
38935	Páska samolepící FESTA 50mmx20m sádrokarton	50mm	20m
38937	Páska samolepící FESTA 50mmx45m sádrokarton	50mm	45m
38939	Páska samolepící FESTA 50mmx90m sádrokarton	50mm	90m
38940	Páska samolepící FESTA 50mmx153m sádrokarton	50mm	153m

Materiál

Vyztužení - mřížka

Lepidlo – akrylátové lepidlo

Vazba – Leno (perlinková vazba)

Barva

Bílá

Vlastnosti

		Hodnota	Jednotka	Tolerance
Velikost mřížky	vlečné	8	Mřížka/palec	+/- 8%
	útek	6	Mřížka/palec	+/- 8%
Lepidlo		≥ 100	vteřina	-
Prodloužení		≥ 0,8	%	-
Pevnost v tahu	vlečné	≥ 9	N/mm	-
	útek	≥ 9	N/mm	-
Finální váha		48,5	g/m2	+/- 5g/m2

Aplikace: Pro napojování spár sádrokartonových desek, pro jejich opravy (trhliny a praskliny)**Výhody:**

Nenatahuje a nezmenšuje se, je stabilní

Vyrovná a odolná vůči většině chemikálií a rozpouštědům

Neskluzná

Podmínky skladování:

Páska by měla být skladována v originálním balení mimo dopad přímého slunečního záření a umístěna na čistém a suchém místě při teplotě 21°C a 50% vlhkosti.

Příprava podkladu:

Podklad musí být očištěn, zbaven všech nesoudržných částí jako je prach, mastnota a další nečistoty.

Likvidace odpadu:

Postupujte podle zákona č. 185/2001 Sb., o odpadech, v platném znění.

Uvedené informace a poskytnuté údaje vycházejí z naší vlastní zkušenosti, výzkumu a objektivního testování a předpokládáme, že jsou spolehlivé a přesné. V praxi nelze vzhledem k rozdílným v materiálech, podkladech a ve skutečných podmínkách v daném místě vyvozovat z těchto informací ani z písemných doporučení či jiného poskytnutého poradenství žádnou záruku za prodejnost či vhodnost k určitému účelu ani žádnou odpovědnost vyplývající z jakéhokoli právního vztahu. Firma nemůže být odpovědná za žádné škody, a to ani přímo nebo nepřímo v důsledku použití produktů uvedených v tomto dokumentu. Každý uživatel je povinen se přesvědčit o vhodnosti použití vlastním testem na malé části povrchu, zda je výrobek vhodný pro zamýšlené použití a účel. Společnost si vyhrazuje právo změnit vlastnosti svých výrobků. Uživatelé jsou vždy povinni prostudovat si poslední verzi technického listu k danému výrobku, jehož kopie zašleme na vyžádání nebo jsou k dispozici na www.levior.cz.

TECHNICAL DATA SHEET AND MANUAL

Item No.	Description	Width	Lenght
38935	Self-adhesive tape FESTA 50mmx20m plasterboard	50mm	20m
38937	Self-adhesive tape FESTA 50mmx45m plasterboard	50mm	45m
38939	Self-adhesive tape FESTA 50mmx90m plasterboard	50mm	90m
38940	Self-adhesive tape FESTA 50mmx153m plasterboard	50mm	153m

Material:

Reinforcement - grid

Glue - acrylic glue

Binding - Leno (pearl binding)

Color:

White

Physical properties:

		Value	Unit	Tolerance
Grid size	tow	8	Grid/inch	+/- 8%
	weft	6	Grid/inch	+/- 8%
Glue		≥ 100	second	-
Extension		≥ 0,8	%	-
Tensile strength	tow	≥ 9	N/mm	-
	weft	≥ 9	N/mm	-
Final weight		48,5	g/m2	+/- 5g/m2

Application: Suitable for connecting joints of plasterboard sheets, for their repairs (cracks and fissures)

Advantages:

Does not stretch or shrink, it is stable

Highly resistant to most chemicals and solvents

Non-slip

Storage and usage conditions:

The tape should be stored in its original packaging away from direct sunlight and in a clean, dry place at a temperature of 21°C and 50% humidity.

Surface preparation:

The surface must be cleaned, free from all loose parts such as dust, grease and other impurities.

Waste disposal:

Follow law No. 185/2001 Coll., about waste, as amended.

The information and data provided are based on our own experience, research and objective testing and are believed to be reliable and accurate. In practice, due to differences in materials, substrates and actual conditions in a given location, no warranty of merchantability or fitness for a particular purpose or any liability arising from any legal relationship can be inferred from this information or from written recommendations or other advice provided. The company cannot be held liable for any damages, either directly or indirectly, resulting from the use of the products listed in this document. Each user is obliged to satisfy themselves about the suitability of the use by testing a small part of the surface, whether the product is suitable for the intended use and purpose. The company reserves the right to change the properties of its products. Users are always obliged to study the latest version of the technical data sheet for the given product, copies of which will be sent on request or are available at www.levior.cz.